







## Systems







- 4 coats *Cetol TSI Satin plus*

## Products

### Sikkens TSI Satin plus Varnish

Transparent, matt finish for interior wood surfaces, based on oil alkyd resin. It accentuates the natural grain, colour and texture of all timbers and provides a

	18m <sup>2</sup> dressed timber
	Thin 5% maximum first coat with white spirits.
	24 hrs at 20°C / 65% relative humidity
	45 microns wet
	Application temperature 5-25°C
	Mineral turpentine

Key	
	Practical coverage in m <sup>2</sup> /ltr per coat, depending on density of timber.
	Thinning %
	Drying time/Recoat after ... hrs
	Film thickness
	Application temperature °C
	Brush clean up

hardwearing finish for doors, cabinets, furniture, etc. Abrasion resistant varnish. Resistant to water, soap, domestic chemicals and alcohol spills. **Use:** Suitable for most types of timber, as a stand alone 4 coat system on bench tops, shelves, skirting, panelling, furniture, doors etc. Also commonly used as the finishing coats on timber that has been stained with **Cetol HLSe**. **Application:** Stir well. **Cetol TSI Satin plus** is a thixotropic product and requires a vigorous beating action, as this will cause the product to thin by itself. Apply to clean, dry sound

substrate. Brush application recommended; apply at **45 microns wet**. Light cut back between coats. See Product Data Sheet for full details.

### Sikkens Oplusser

**High solvent degreaser.** Oplusser is used for the strip wiping of surfaces to be coated and to assist with the removal of natural resins, contaminants and residue.

**See Product Data Sheet for full details on all products.**

## Directions

- Water borne products are unsuitable for bench tops.
- Thoroughly stir product with flat-ended stirrer for 5 minutes before each use, ensuring that the bottom of the tin is well scraped. Stir at regular intervals during use.. **Cetol TSI Satin plus** is a thixotropic product and must be well beaten when stirring, as this action will thin the product.
- Apply by brush or spray.
- Experimentation in the method of application may be required to achieve the desired effect.
- Do not apply in direct sunlight or excessive heat.
- Bench top should be installed to check for clearances and fitting. All trims should be fully fitted to ensure a good fit and that no alterations are required after coating. The bench top should be removed immediately for coating.
- All timber being coated must have a minimum 3mm round on all edges. Ensure holes cut for the sinks are clean cut and are all rounded.
- All faces of the bench top, edges, rebates, end grains and behind all hardware must be sealed with at least 3 coats.
- Do not apply in high humidity as this may cause the varnish to bloom.
- Keep airflow to a minimum as this reduces working time.
- First coat can be thinned up to 10%. Subsequent coats are better applied unthinned. (Thin only if required to aid settling but keep to a minimum).
- Ensure all timber to be coated has moisture content of 12% or lower.
- Ensure the timber surface to be coated is cool to the touch.
- Ensure surface of timber is dry, free of grease, dirt, mould and oil.
- All dressed timber should be lightly sanded with fine grade paper to remove machining marks, handprints, glue etc. Always sand along the grain and never across. Remove sanding dust.
- Degrease all timber prior to coating using **Sikkens Oplusser**.
- Oily resinous timbers require extra preparation. Please check prior to coating.
- Ensure coats are thoroughly dry before applying further coats.
- Lightly cut back with fine grade sandpaper between coats as this will ensure a smooth finish. Any reduction in film thickness will result in a reduction of the durability of the system.

## Directions (continued)

- Do not mask coatings until full cure has taken place, approximately 7-14 days depending on drying conditions.
- Follow all the masking tape manufacturer's requirements. Ensure masking tape is removed as soon as possible and inside the manufacturer's specified time limit.
- Do not apply to surfaces previously treated with linseed oil, polyurethane, waxes or stains.
- Dispose of all materials safely. Do not dispose of any material down stormwater systems. Contact your local council for correct disposal methods.
- When undertaking any work always follow good trade, health and safety practices.
- Follow all good coating practices.

## Life span

- 5–20 years depending on use, area coated and the desired look required by the user.
- **Recommended film thickness.** The recommended film thickness is an integral part of the specification and durability. The systems are based on application of the coatings to the recommended film thickness of each coating in the system. Over brushing of the coating, and therefore insufficient protection of the substrate, is the most common cause of inferior coating performance.

## Please Note

- Every care is taken to ensure that the information provided in this data sheet is accurate. Jac Jay Limited is unable to guarantee results as it has no control over the conditions under which products are applied, the substrate or the application. The customer has to determine the suitability of the delivered products or information for its intended purpose.